

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 23/10, C08F 23/12, 23/16	A1	(11) International Publication Number: WO 99/07788 (43) International Publication Date: 18 February 1999 (18.02.99)
(21) International Application Number: PCT/US98/09802 (22) International Filing Date: 23 July 1998 (23.07.98) (30) Priority Data: 08/910,001 12 August 1997 (12.08.97) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US). (72) Inventors: DATTA, Sudhin; 2203 Driscoll Street, Houston, TX 77019 (US). GADKARI, Avinash, C.; 13827 Rosebranch Court, Houston, TX 77059 (US). COZEWITH, Charles; 4810 Welford Drive, Bellaire, TX 77401 (US). (74) Agents: SCHNEIDER, John, E. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).		(81) Designated States: AU, BR, CA, CN, JP, KR, MX, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: THERMOPLASTIC POLYMER BLENDS OF ISOTACTIC POLYPROPYLENE AND ALPHA-OLEFIN/PROPYLENE COPOLYMERS (57) Abstract Thermoplastic polymer blend compositions comprising an isotactic polypropylene component and an alpha-olefin and propylene copolymer, said copolymer comprising crystallizable alpha-olefin sequences. In a preferred embodiment, improved thermoplastic polymer blends are provided comprising from about 35 % to about 85 % isotactic polypropylene and from about 30 % to about 70 % of an ethylene and propylene copolymer, wherein said copolymer comprises isotactically crystallizable propylene sequences and is predominantly propylene. The resultant blends manifest compatibility characteristics, increased tensile strength, and improved process characteristics, e.g., a single melting point.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**THERMOPLASTIC POLYMER BLENDS OF ISOTACTIC
POLYPROPYLENE AND ALPHA-OLEFIN/PROPYLENE COPOLYMERS**

5 FIELD OF THE INVENTION

The invention relates to polymer blends of at least two polymers having surprising properties when compared to the properties of the individual polymers prior to blending. More specifically, the invention relates to blends of thermoplastic polymers, e.g., according to one embodiment, isotactic
10 polypropylene and an olefin copolymer. The invention further relates to thermoplastic polymer blends comprising isotactic polypropylene and, according to one embodiment, a copolymer of ethylene and propylene, wherein the copolymer comprises isotactically crystallizable alpha-olefin sequences. In addition, the invention relates to methods for making the above polymers and
15 blends thereof.

BACKGROUND OF THE INVENTION

Although blends of isotactic polypropylene and ethylene propylene rubber are well known in the prior art, prior art Ziegler-Natta catalyst systems could only
20 produce ethylene propylene rubber compositions with greater than 30% by weight ethylene at practical, economic polymerization conditions. There exists a need for polymeric materials which have advantageous processing characteristics while still providing suitable end properties to articles formed therefrom, e.g., tensile and impact strength. Copolymers and blends of polymers have been developed to try
25 and meet the above needs. U.S. Patent No. 3,882,197 to Fritz et al. describes blends of stereoregular propylene/alpha-olefin copolymers, stereoregular propylene, and ethylene copolymer rubbers. In U.S. Patent 3,888,949 Chi-Kai Shih, assigned to E I DuPont, shows the synthesis of blend compositions containing isotactic polypropylene and copolymers of propylene and an alpha-

olefin, containing between 6 - 20 carbon atoms, which have improved elongation and tensile strength over either the copolymer or isotactic polypropylene. Copolymers of propylene and alpha-olefin are described wherein the alpha-olefin is hexene, octene or dodecene. However, the copolymer is made with a heterogeneous titanium catalyst which makes copolymers which are non-uniform in compositional distribution and typically broad in molecular weight distribution. Compositional distribution is a property of copolymers where there exists statistically significant intermolecular or intramolecular difference in the composition of the polymer. Methods for measuring compositional distribution are described later. The presence of intramolecular compositional distribution is described in US Patent No. 3,888,949 by the use of the term "block" in the description of the polymer where the copolymer is described as having "sequences of different alpha-olefin content." Within the context of the invention described above the term sequences describes a number of olefin monomer residues catenated together by chemical bonds and obtained by a polymerization procedure.

In U.S. Patent 4,461,872, A.C.L. Su improved on the properties of the blends described in U.S. Patent 3,888,949 by using another heterogeneous catalyst system. However, the properties and compositions of the copolymer with respect to either the nature and type of monomers (alpha-olefin containing 6 - 20 carbon atoms) or the blocky heterogeneous intra/inter molecular distribution of the alpha-olefin in the polymer have not been resolved since the catalysts used for these polymerization of propylene and alpha-olefin are expected to form copolymers which have statistically significant intermolecular and intramolecular compositional differences.

In two successive publications in the journal of *Macromolecules*, 1989, v22, pages 3851-3866, J.W. Collette of E. I. DuPont has described blends of isotactic polypropylene and partially atactic polypropylene which have desirable

tensile elongation properties. However, the partially atactic propylene has a broad molecular weight distribution as shown in Figure 8 of the first publication. The partially atactic polypropylene is also composed of several fractions, which differ in the level of tacticity of the propylene units as shown by the differences in the solubility in different solvents. This is shown by the corresponding physical decomposition of the blend which is separated by extraction with different solvents to yield individual components of uniform solubility characteristics as shown in Table IV of the above publications.

In U.S. Patent Nos. 3,853,969 and 3,378,606, E.G. Kontos discloses the formation of *in situ* blends of isotactic polypropylene and "stereo block" copolymers of propylene and another olefin of 2 to 12 carbon atoms, including ethylene and hexene. The copolymers of this invention are necessarily heterogeneous in intermolecular and intramolecular composition distribution. This is demonstrated by the synthesis procedures of these copolymers which involve sequential injection of monomer mixtures of different compositions to synthesize polymeric portions of analogously different compositions. In addition, Fig. 1 of both patents shows that the "stereo block" character, which is intra or intermolecular compositional differences in the context of the description of the present invention, is essential to the benefit of the tensile and elongation properties of the blend. In situ blends of isotactic polypropylene and compositionally uniform random ethylene propylene copolymers have poor properties. Moreover, all of these compositions either do not meet all of the desired properties for various applications, and/or involve costly and burdensome process steps to achieve the desired results.

Similar results are anticipated by R. Holzer and K. Mehnert in U.S. Patent 3,262,992 assigned to Hercules wherein the authors disclose that the addition of a stereoblock copolymer of ethylene and propylene to isotactic polypropylene leads

to improved mechanical properties of the blend compared to isotactic polypropylene alone. However, these benefits are described only for the stereoblock copolymers of ethylene and propylene. The synthesis of these copolymers is designed around polymerization conditions where the polymer chains are generated in different compositions of ethylene and propylene achieved by changing, with time, the monomer concentrations in the reactor. This is shown in examples 1 and 2. The stereoblock character of the polymer is graphically shown in the molecular description (column 2, line 65) and contrasted with the undesirable random copolymer (column 2, line 60). The presence of stereoblock character in these polymers is shown by the high melting point of these polymers, which is much greater than the melting point of the second polymer component in the present invention, shown in Table 1, as well as the poor solubility of these hetero block materials, as a function of the ethylene wt % of the material as shown in Table 3.

It would be desirable to produce a blend of a crystalline polymer, hereinafter referred to as the "first polymer component," and a crystallizable polymer, hereinafter referred to as the "second polymer component", having advantageous processing characteristics while still providing end products made from the blend composition having the desired properties, i.e., increased tensile strength, elongation, and overall toughness. The first polymer component (abbreviated as "FPC" in the Tables below) and the second polymer component (abbreviated as "SPC" in the Tables below). Indeed, there is a need for an entirely polyolefin composition which is thermally stable, heat resistant, light resistant and generally suitable for thermoplastic elastomer (TPE) applications which has advantageous processing characteristics. Such an entirely polyolefin composition would be most beneficial if the combination of the first polymer component and the second polymer component were significantly different in mechanical

properties than the compositionally weighted average of the corresponding properties of first polymer component and second polymer component alone. We anticipate, while not meant to be limited thereby, that the potency of the second polymer component may be increased if it only consists of one or two polyolefin copolymers material defined by uniform intramolecular and intermolecular composition and microstructure.

The term "crystalline," as used herein for first polymer component, characterizes those polymers which possess high degrees of inter- and intramolecular order, and which melt higher than 110°C and preferably higher than 115°C and have a heat of fusion of at least 75 J/g, as determined by DSC analysis. And, the term "crystallizable," as used herein for second polymer component, describes those polymers or sequences which are mainly amorphous in the undeformed state, but upon stretching or annealing, crystallization occurs. Crystallization may also occur in the presence of the crystalline polymer such as first polymer component. These polymers have a melting point of less than 105°C or preferably less than 100°C and a heat of fusion of less than 75 J/g as determined by DSC.

SUMMARY OF THE INVENTION

The present invention, according to one embodiment, is directed to the use of chiral metallocene catalysts to (1) readily produce second polymer component being ethylene propylene rubber compositions with about 4 wt % to about 25 wt % ethylene, and (2) readily produce second polymer component compositions containing isotactic propylene sequences long enough to crystallize. Thus, the invention is directed, according to one embodiment, to semicrystalline materials (second polymer component), which when blended with isotactic polymers (first polymer component), show an increased level of compatibility between the

ethylene propylene and isotactic polypropylene phases. While not meant to be limited thereby, we believe the increased compatibility is due to the similarity of the composition of the first polymer component and all of the second polymer component. Thus, the uniformity of the intra- and inter-molecular composition of the second polymer component is of importance. In particular, it is important that substantially all of the components of the second polymer component be within the narrow composition range of ethylene and propylene defined above. In addition, the presence of isotactic propylene sequences in the second polymer component is of benefit for the improved adhesion of the domains of the first polymer component and the second polymer component in the polymer blend composition. As a result, blends of isotactic polypropylene with ethylene propylene copolymers according to the invention, have improved physical properties as compared to isotactic polypropylene blends with prior art ethylene propylene rubbers.

According to one embodiment, a composition of the present invention comprises a blend of at least a first polymer component and a second polymer component. The blend comprises greater than about 2% by weight of the first polymer component comprising an alpha-olefin propylene copolymer containing isotactic polypropylene crystallinity with a melting point of about 115°C to about 170°C. The blend also contains a second polymer component comprising a copolymer of propylene and at least one other alpha-olefin having less than 6 carbon atoms, and preferably 2 carbon atoms. The second polymer component copolymer of the invention, according to one embodiment, comprises isotactically crystallizable propylene sequences and greater than 75% by weight propylene and preferably greater than 80% by weight propylene.

According to another embodiment, a thermoplastic polymer blend composition of the invention comprises a first polymer component and a second

polymer component. The first polymer component comprises isotactic polypropylene, and is present in an amount of about 2% to about 95% by weight and more preferably 2% to 70% by weight of the total weight of the blend. The first polymer component may also be comprised of commonly available isotactic polypropylene compositions referred to as impact copolymer or reactor copolymer. However these variations in the identity of the first polymer component are acceptable in the blend only to the extent that all of the components of the first polymer component are substantially similar in composition and the first polymer component is within the limitations of the crystallinity and melting point indicated above. This first polymer component may also contain additives such as flow improvers, nucleators and antioxidants which are normally added to isotactic polypropylene to improve or retain properties. All of these polymers are referred to as the first polymer component.

The second polymer component is a thermoplastic comprising a random copolymer of ethylene and propylene having a melting point by DSC of 25°C to 105°C, preferably in the range 25°C to 90°C, more preferably in the range of 40°C to 90° C and an average propylene content by weight of at least 75% and more preferably at least 80%. The second polymer component is made with a polymerization catalyst which forms essentially or substantially isotactic polypropylene, when all or substantially all propylene sequences in the second polymer component are arranged isotactically. This copolymer contains crystallizable propylene sequences due to the isotactic polypropylene. The second polymer component is statistically random in the distribution of the ethylene and propylene residues along the chain. Quantitative evaluation of the randomness of the distribution of the ethylene and propylene sequences may be obtained by consideration of the experimentally determined reactivity ratios of the second polymer component. We believe that the second polymer component is random in

the distribution of ethylene and propylene sequences since (1) it is made with a single sited metallocene catalyst which allows only a single statistical mode of addition of ethylene and propylene and (2) it is made in a well mixed, continuous monomer feed stirred tank polymerization reactor which allows only a single
5 polymerization environment for substantially all of the polymer chains of the second polymer component. Thus there is substantially no statistically significant difference in the composition of the second polymer component either among two polymer chains or along any one chain.

The ratio of the first polymer component to the second polymer component
10 of the blend composition of the present invention may vary in the range of 2:98 to 95:5 by weight and more preferably in the range 2:98 to 70:30 by weight.

According to another embodiment of the present invention, the second polymer component may contain small quantities of a non-conjugated diene to aid in the vulcanization and other chemical modification of the blend of the first
15 polymer component and the second polymer component. The amount of diene is limited to be no greater than 10 wt% and preferably no greater than 5 wt %. The diene may be selected from the group consisting of those which are used for the vulcanization of ethylene propylene rubbers and preferably ethyldiene norbornene, vinyl norbornene and dicyclopentadiene.

20 According to still a further embodiment, the invention is directed to a process for preparing thermoplastic polymer blend compositions. The process comprises: (a) polymerizing propylene or a mixture of propylene and one or more monomers selected from C₂ or C₄ - C₁₀ alpha olefins in the presence of a polymerization catalyst wherein a substantially isotactic propylene polymer
25 containing at least about 90% by weight polymerized propylene is obtained; (b) polymerizing a mixture of ethylene and propylene in the presence of a chiral metallocene catalyst, wherein a copolymer of ethylene and propylene is obtained

comprising up to about 25% by weight ethylene and preferably up to 20% by weight ethylene and containing isotactically crystallizable propylene sequences; and (c) blending the propylene polymer of step (a) with the copolymer of step (b) to form a blend.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS OF THE INVENTION

The blend compositions of the present invention generally are comprised of two components: (1) a first polymer component comprising isotactic polypropylene, and (2) a second polymer component comprising an alpha-olefin (other than propylene) and propylene copolymer.

The First Polymer Component (FPC)

In accordance with the present invention, the first thermoplastic polymer component (first polymer component), i.e., the polypropylene polymer component may be homopolypropylene, or copolymers of propylene, or some blends thereof. The polypropylene used in the present blends can vary widely in form. For example, substantially isotactic polypropylene homopolymer can be used or the polypropylene can be in the form of a copolymer containing equal to or less than about 10 weight percent of other monomer, i.e., at least about 90% by weight propylene. Further, the polypropylene can be present in the form of a graft or block copolymer, in which the blocks of polypropylene have substantially the same stereoregularity as the propylene-alpha-olefin copolymer, so long as the graft or block copolymer has a sharp melting point above about 110°C and preferably above 115°C and more preferably above 130°C, characteristic of the stereoregular propylene sequences. The first polymer component of the present invention is predominately crystalline, i.e., it has a melting point generally greater than about 110°C, preferably greater than about 115°C, and most preferably greater than about 130°C. The propylene polymer component may be a combination of homopolypropylene, and/or random, and/or block copolymers as described herein. When the above propylene polymer component is a random copolymer, the percentage of the copolymerized alpha-olefin in the copolymer is, in general, up to

about 9% by weight, preferably about 2% to about 8% by weight, most preferably about 2% to about 6% by weight. The preferred alpha-olefins contain 2 or from 4 to about 12 carbon atoms. The most preferred alpha-olefin is ethylene. One, or two or more alpha-olefins can be copolymerized with propylene.

5 Exemplary alpha-olefins may be selected from the group consisting of ethylene; butene-1; pentene-1,2-methylpentene-1,3-methylbutene-1; hexene-1,3-methylpentene-1,4-methylpentene-1,3,3-dimethylbutene-1; heptene-1; hexene-1; methylhexene-1; dimethylpentene-1 trimethylbutene-1; ethylpentene-1; octene-1; methylpentene-1; dimethylhexene-1; trimethylpentene-1; ethylhexene-1;
10 methylethylpentene-1; diethylbutene-1; propylpentane-1; decene-1; methylnonene-1; nonene-1; dimethyloctene-1; trimethylheptene-1; ethyloctene-1; methylethylbutene-1; diethylhexene-1; dodecene-1 and hexadodecene-1.

The thermoplastic polymer blend compositions of the present invention may comprise from about 2% to about 95% by weight of first polymer component.
15 According to a preferred embodiment, the thermoplastic polymer blend composition of the present invention may comprise from about 2% to about 70% by weight of the first polymer component. According to the most preferred embodiment, the compositions of the present invention may comprise from about 5% to about 70% by weight of the first polymer component.

20 There is no particular limitation on the method for preparing this propylene polymer component of the invention. However, in general, the polymer is a propylene homopolymer obtained by homopolymerization of propylene in a single stage or multiple stage reactor. Copolymers may be obtained by copolymerizing propylene and an alpha-olefin having 2 or from 4 to about 20 carbon atoms,
25 preferably ethylene, in a single stage or multiple stage reactor. Polymerization methods include high pressure, slurry, gas, bulk, or solution phase, or a combination thereof, using a traditional Ziegler-Natta catalyst or a single-site,

metallocene catalyst system. The catalyst used is preferably one which has a high isospecificity. Polymerization may be carried out by a continuous or batch process and may include use of chain transfer agents, scavengers, or other such additives as deemed applicable.

5

The Second Polymer Component (SPC)

The second polymer component of the polymer blend compositions of the present invention comprises a copolymer of propylene and another alpha-olefin having less than 6 carbon atoms, preferably ethylene. Optionally, the second component of the composition of the present invention may further comprise, in addition to the above mentioned, amounts of a diene. The second polymer component of the present inventive composition preferably, according to one embodiment, comprises a random copolymer having a narrow compositional distribution. While not meant to be limited thereby, it is believed that the narrow composition distribution of the second polymer component is important. The intermolecular composition distribution of the polymer is determined by thermal fractionation in a solvent. A typical solvent is a saturated hydrocarbon such as hexane or heptane. This thermal fractionation procedure is described below. Typically, approximately 75% by weight and more preferably 85% by weight of the polymer is isolated as a one or two adjacent, soluble fraction with the balance of the polymer in immediately preceding or succeeding fractions. Each of these fractions has a composition (wt% ethylene content) with a difference of no greater than 20 wt.% (relative) and more preferably 10 wt.% (relative) of the average wt% ethylene content of the whole second polymer component. The second polymer component is narrow in compositional distribution if it meets the fractionation test outlined above.

25

In all second polymer component, the number and distribution of ethylene residues is consistent with the random statistical polymerization of ethylene, propylene and optional amounts of diene. In stereoblock structures, the number of monomer residues of any one kind adjacent to one another is greater than
5 predicted from a statistical distribution in random copolymers with a similar composition. Historical polymers with stereoblock structure have a distribution of ethylene residues consistent with these blocky structures rather than a random statistical distribution of the monomer residues in the polymer. The intramolecular composition distribution of the polymer may be determined by C-
10 ¹³ NMR which locates the ethylene residues in relation to the neighboring propylene residue. A more practical and consistent evaluation of the randomness of the distribution of the ethylene and propylene sequences may be obtained by the following consideration. We believe that the second polymer component is random in the distribution of ethylene and propylene sequences since (1) it is
15 made with a single sited metallocene catalyst which allows only a single statistical mode of addition of ethylene and propylene and (2) it is made in a well mixed, continuous monomer feed stirred tank polymerization reactor which allows only a single polymerization environment for substantially all of the polymer chains of the second polymer component.

20 The second polymer component preferably, according to one embodiment of the invention, has a single melting point. The melting point is determined by DSC. Generally, the copolymer second component of the present invention has a melting point below the first polymer component of the blend typically between about 105°C and 25°C. Preferably, the melting point of second polymer
25 component is between about 90°C and 25°C. Most preferably, according to one embodiment of the present invention, the melting point of the second polymer component of the composition of the present invention is between 90°C and 40°C.

The second polymer component preferably has a narrow molecular weight distribution (MWD) between about 1.8 to about 5.0, with a MWD between about 2.0 to about 3.2 preferred.

The second polymer component of the present inventive composition
5 comprises isotactically crystallizable alpha-olefin sequences, e.g., preferably propylene sequences (NMR). The crystallinity of the second polymer component is, preferably, according to one embodiment, from about 2% to about 65% of homoisotactic polypropylene, preferably between 5% to 40%, as measured by the heat of fusion of annealed samples of the polymer.

10 According to another embodiment of the present invention, the second polymer component of the composition comprises from about 5% to about 25% by weight alpha-olefin, preferably from about 6% to about 20% by weight alpha-olefin, and most preferably, it comprises from about 6% to about 18% by weight alpha-olefin and even more preferably between 10% to 16% by alpha-olefin.
15 These composition ranges for the second polymer component are dictated by the object of the present invention. At alpha-olefin compositions lower than the above lower limits for the second polymer component, the blends of the first polymer component and second polymer component are hard and do not have the favorable elongation properties of the blends of the present invention. At alpha-
20 olefin compositions higher than the above higher limits for the second polymer component, the blends of the second polymer component and the first polymer component do not have the favorable tensile properties of the blends of the present invention. It is believed, while not meant to be limited thereby, the second polymer component needs to have the optimum amount of isotactic polypropylene
25 crystallinity to crystallize with the first polymer component for the beneficial effects of the present invention. As discussed above, the preferred alpha-olefin is ethylene.

The compositions of the present invention may comprise from about 5% to about 98% by weight of the second polymer component. According to one preferred embodiment, the compositions of the present invention may comprise from about 30% to about 98% by weight of the second polymer component. Most preferably, the compositions of the present invention comprise from about 30% to about 95% by weight of the second polymer component.

Generally, without limiting in any way the scope of the invention, one means for carrying out a process of the present invention for the production of the copolymer second polymer component is as follows: (1) liquid propylene is introduced in a stirred-tank reactor, (2) the catalyst system is introduced via nozzles in either the vapor or liquid phase, (3) feed ethylene gas is introduced either into the vapor phase of the reactor, or sparged into the liquid phase as is well known in the art, (4) the reactor contains a liquid phase composed substantially of propylene, together with dissolved alpha-olefin, preferably ethylene, and a vapor phase containing vapors of all monomers, (5) the reactor temperature and pressure may be controlled via reflux of vaporizing propylene (autorefrigeration), as well as by cooling coils, jackets, etc., (6) the polymerization rate is controlled by the concentration of catalyst, temperature, and (7) the ethylene (or other alpha-olefin) content of the polymer product is determined by the ratio of ethylene to propylene in the reactor, which is controlled by manipulating the relative feed rates of these components to the reactor.

For example, a typical polymerization process consists of a polymerization in the presence of a catalyst comprising a bis (cyclopentadienyl) metal compound and either 1) a non-coordinating compatible anion activator, or 2) an alumoxane activator. According to one embodiment of the invention, this comprises the steps of contacting ethylene and propylene with a catalyst in a suitable polymerization diluent, said catalyst comprising, for example, according to a preferred

embodiment, a chiral metallocene catalyst, e.g., a bis (cyclopentadienyl) metal compound, as described in U.S. Patent No. 5,198,401 which is herein incorporated by reference for purposes of U.S. practices and an activator. The activator used may be an alumoxane activator or a non-coordination compatible anion activator.

5 The alumoxane activator is preferably utilized in an amount to provide a molar aluminum to metallocene ratio of from about 1:1 to about 20,000:1 or more. The non-coordinating compatible anion activator is preferably utilized in an amount to provide a molar ratio of biscyclopentadienyl metal compound to non-coordinating anion of 10:1 to about 1:1. The above polymerization reaction is conducted by
10 reacting such monomers in the presence of such catalyst system at a temperature of from about -100°C to about 300°C for a time of from about 1 second to about 10 hours to produce a copolymer having a weight average molecular weight of from about 5,000 or less to about 1,000,000 or more and a molecular weight distribution of from about 1.8 to about 4.5.

15 While the process of the present invention includes utilizing a catalyst system in the liquid phase (slurry, solution, suspension or bulk phase or combination thereof), according to other embodiments, high-pressure fluid phase or gas phase polymerization can also be utilized. When utilized in a gas phase, slurry phase or suspension phase polymerization, the catalyst systems will
20 preferably be supported catalyst systems. See, for example, U.S. Patent No. 5,057,475 which is incorporated herein by reference for purposes of U.S. practice. Such catalyst systems can also include other well-known additives such as, for example, scavengers. See, for example, U.S. Patent No. 5,153,157 which is incorporated herein by reference for purposes of U.S. practices. These processes
25 may be employed without limitation of the type of reaction vessels and the mode of conducting the polymerization. As stated above, and while it is also true for systems utilizing a supported catalyst system, the liquid phase process comprises

the steps of contacting ethylene and propylene with the catalyst system in a suitable polymerization diluent and reacting the monomers in the presence of the catalyst system for a time and at a temperature sufficient to produce an ethylene-propylene copolymer of the desired molecular weight and composition.

5 It is understood in the context of the present invention that, in one embodiment, more than one-second polymer component may be used in a single blend with a first polymer component. Each of the second polymer component components is described above and the number of second polymer component in this embodiment is less than three and more preferably, two. In this embodiment
10 of the invention the second polymer components differ in the alpha-olefin content with one being in the range of 5 wt% to 9 wt% alpha-olefin while the other is in the range of 10 wt% to 22 wt% alpha-olefin. The preferred alpha-olefin is ethylene. It is believed that the use of two-second polymer component in conjunction with a single first polymer component leads to beneficial
15 improvements in the tensile-elongation properties of the blends

The Blend of First and Second Polymer Components

The copolymer blends of first polymer component and second polymer component of the instant invention may be prepared by any procedure that
20 guarantees the intimate admixture of the components. For example, the components can be combined by melt pressing the components together on a Carver press to a thickness of about 0.5 millimeter (20 mils) and a temperature of about 180°C, rolling up the resulting slab, folding the ends together, and repeating the pressing, rolling, and folding operation about 10 times. Internal mixers are
25 particularly useful for solution or melt blending. Blending at a temperature of about 180°C to 240°C in a Brabender Plastograph for about 1 to 20 minutes has been found satisfactory. Still another method that may be used for admixing the

components involves blending the polymers in a Banbury internal mixer above the flux temperature of all of the components, e.g., 180°C for about 5 minutes. The complete admixture of the polymeric components is indicated by the narrowing of the crystallization and melting transitions characteristic of the polypropylene crystallinity of the components to give a single or a small range crystallization and melting points for the blend. These batch-mixing procedures are typically supplanted by continuous mixing processes in the industry. These processes are well known in the art and include single and twin screw mixing extruders, static mixers for mixing molten polymer streams of low viscosity, impingement mixers, as well as other machines and processes, designed to disperse the first polymer component and the second polymer component in intimate contact.

The polymer blends of the instant invention exhibit a remarkable combination of desirable physical properties. The incorporation of as little as 5% first polymer component in the propylene/alpha-olefin copolymers increases the propylene sequence melting point or the polymer softening point but, more significantly, reduces the range as compared to the propylene/alpha-olefin copolymer. In addition, the incorporation of first polymer component in accordance with the instant invention nearly eliminates the stickiness caused by the propylene/alpha-olefin copolymer. Further, the thermal characteristics of the copolymer blends are markedly improved over those of the second polymer component which is the propylene/alpha-olefin copolymers.

The crystallization temperature and the melting point of the blends are changed as a result of the blending operation. In an embodiment of the invention, the blend of first polymer component and second polymer component has single crystallization temperature and melting point. These temperatures are higher than the corresponding temperatures for the second polymer component and close to that of the first polymer component. In other embodiments, the second polymer

component and the first polymer component have distinct melting and crystallization temperatures but have these temperatures closer together than would be expected for a combination of the second polymer component and the first polymer component. In all these cases the glass transition temperature of the second polymer component is retained in the polymer blend. This favorable combination of thermal properties permits their satisfactory use in injection molding operations without the orientation previously encountered. Injection molded articles prepared from the instant copolymer blends accordingly exhibit excellent long-term dimensional stability. The advantages referred to above are obtained without the need of elaborate purification of the propylene/alpha-olefin copolymer or the tedious preparation of a carefully structured block copolymer. Further, by the use of the second polymer component and the first polymer component, a blend can be obtained with a lower glass transition temperature than would be expected for a random copolymer of the same composition as the blend. In particular, the glass transition temperature of the blend is closer to that of the second polymer component and lower than the glass transition temperature of the first polymer component. This can be accomplished without an exceptionally high alpha-olefin content in the polymer blend which we believe, while not meant to be limited thereby, would lead to degradation of the tensile-elongation properties of the blend.

The mechanism by which the desirable characteristics of the present copolymer blends are obtained is not fully understood. However, it is believed to involve a co-crystallization phenomenon between propylene sequences of similar stereoregularity in the various polymeric components, which results in one embodiment, a single crystallization temperature and a single melting temperature of the copolymer blend which is higher than those of the second polymer component which is the propylene/alpha-olefin component of the blend. In

another embodiment, the combination of the first polymer component and the second polymer component has a melting point closer together than would be expected on a comparison of the properties of the individual components alone. It is surprising that in the one embodiment, the blend has a single crystallization temperature and a single melting temperature, since it would be expected by those skilled in the art that the blending of two crystalline polymers would result in a double crystallization temperature as well as a double melting temperature reflecting the two polymeric components. However, the intimate blending of the polymers having the required crystallinity characteristics apparently results in a crystallization phenomenon that modifies the other physical properties of the propylene/alpha-olefin copolymer, thus measurably increasing its commercial utility and range of applications.

While the above discussion has been limited to the description of the invention in relation to having only components one and two, as will be evident to those skilled in the art, the polymer blend compositions of the present invention may comprise other additives. Various additives may be present in the composition of the invention to enhance a specific property or may be present as a result of processing of the individual components. Additives which may be incorporated include, for example, fire retardants, antioxidants, plasticizers, and pigments. Other additives which may be employed to enhance properties include antiblocking agents, coloring agents, stabilizers, and oxidative-, thermal-, and ultraviolet-light-inhibitors. Lubricants, mold release agents, nucleating agents, reinforcements, and fillers (including granular, fibrous, or powder-like) may also be employed. Nucleating agents and fillers tend to improve rigidity of the article. The list described herein is not intended to be inclusive of all types of additives which may be employed with the present invention. Upon reading this disclosure, those of skill in the art will appreciate other additives may be employed to enhance

properties of the composition. As is understood by the skilled in the art, the polymer blend compositions of the present invention may be modified to adjust the characteristics of the blend as desired.

As used herein, Mooney Viscosity was measured as ML (1+4) at 125°C in
5 Mooney units according to ASTM D1646.

The composition of Ethylene propylene copolymers, which are used as comparative examples, was measured as ethylene Wt% according to ASTM D 3900.

The composition of the second polymer component was measured as
10 ethylene Wt% according to the following technique. A thin homogeneous film of the second polymer component, pressed at a temperature of about or greater than 150°C was mounted on a Perkin Elmer PE 1760 infra red spectrophotometer. A full spectrum of the sample from 600 cm⁻¹ to 400 cm⁻¹ was recorded and the ethylene Wt% of the second polymer component was calculated according to
15 Equation 1 as follows:

$$\text{ethylene Wt\%} = 82.585 - 111.987 X + 30.045X^2$$

wherein X is the ratio of the peak height at 1155 cm⁻¹ and peak height at either
20 722 cm⁻¹ or 732 cm⁻¹, which ever is higher.

Techniques for determining the molecular weight (Mn and Mw) and molecular weight distribution (MWD) are found in U.S. Patent 4,540,753 (Cozewith, Ju, and Verstrate) (which is incorporated by reference herein for purposes of U.S. practices) and references cited therein and in *Macromolecules*,
25 1988, volume 21, p 3360 (Verstrate et al) (which is herein incorporated by reference for purposes of U.S. practice) and references cited therein.

The procedure for Differential Scanning Calorimetry is described as follows. About 6 to 10 mg of a sheet of the polymer pressed at approximately 200°C to 230°C is removed with a punch die. This is annealed at room temperature for 80 to 100 hours. At the end of this period, the sample is placed in
5 a Differential Scanning Calorimeter (Perkin Elmer 7 Series Thermal Analysis System) and cooled to about -50°C to about -70°C. The sample is heated at 20°C/min to attain a final temperature of about 200°C to about 220°C. The thermal output is recorded as the area under the melting peak of the sample which is typically peaked at about 30°C to about 175°C and occurs between the
10 temperatures of about 0°C and about 200°C is measured in Joules as a measure of the heat of fusion. The melting point is recorded as the temperature of the greatest heat absorption within the range of melting of the sample. Under these conditions, the melting point of the second polymer component and the heat of fusion is lower than the first polymer component as outlined in the description
15 above.

Composition distribution of the second polymer component was measured as described below. About 30 gms. of the second polymer component was cut into small cubes about 1/8" on the side. This is introduced into a thick walled glass bottle closed with screw cap along with 50 mg of Irganox1076, an
20 antioxidant commercially available from Ciba - Geigy Corporation. Then, 425 ml of hexane (a principal mixture of normal and ISO isomers) is added to the contents of the bottle and the sealed bottle is maintained at about 23°C for 24 hours. At the end of this period, the solution is decanted and the residue is treated with additional hexane for an additional 24 hours. At the end of this period, the two-
25 hexane solutions are combined and evaporated to yield a residue of the polymer soluble at 23°C. To the residue is added sufficient hexane to bring the volume to 425 ml and the bottle is maintained at about 31°C for 24 hours in a covered

circulating water bath. The soluble polymer is decanted and the additional amount of hexane is added for another 24 hours at about 31°C prior to decanting. In this manner, fractions of the second polymer component soluble at 40°C, 48°C, 55°C and 62°C are obtained at temperature increases of approximately 8°C between stages. Further, increases in temperature to 95°C can be accommodated, if heptane, instead of hexane, is used as the solvent for all temperatures above about 60°C. The soluble polymers are dried, weighed and analyzed for composition, as wt% ethylene content, by the IR technique described above. Soluble fractions obtained in the adjacent temperature increases are the adjacent fractions in the specification above.

EPR in the data tables below is Vistalon 457, sold by the Exxon Chemical Company, Houston TX.

The invention, while not meant to be limited thereby, is further illustrated by the following specific examples:

EXAMPLES

Example 1: Ethylene/propylene copolymerization to form the second polymer component.

Polymerizations were conducted in a 1-liter thermostatted continuous feed stirred tank reactor using hexane as the solvent. The polymerization reactor was full of liquid. The residence time in the reactor was typically 7 - 9 minutes and the pressure was maintained at 400kpa. Hexane, ethene and propene were metered into a single stream and cooled before introduction into the bottom of the reactor. Solutions of all reactants and polymerization catalysts were introduced continuously into the reactor to initiate the exothermic polymerization. Temperature of the reactor was maintained at 41°C by changing the temperature of

the hexane feed and by circulating water in the external jacket. For a typical polymerization, the temperature of feed was about 0°C.

Ethene was introduced at the rate of 45 gms/min and propene was introduced at the rate of 480 gms/min. The polymerization catalyst, dimethyl silyl
5 bridged bis-indenyl Hafnium dimethyl activated 1:1 molar ratio with N', N'-
Dimethyl anilinium-tetrakis(pentafluorophenyl)borate was introduced at the rate
of 0.00897 gms/hr. A dilute solution of triisobutyl aluminum was introduced into
the reactor as a scavenger of catalyst terminators: a rate of approximately 28.48
mol of scavenger per mole of catalyst was adequate for this polymerization. After
10 five residence times of steady polymerization, a representative sample of the
polymer produced in this polymerization was collected. The solution of the
polymer was withdrawn from the top, and then steam distilled to isolate the
polymer. The rate of formation of the polymer was 285.6 gms/hr. The polymer
produced in this polymerization had an ethylene content of 13% , ML@125 (1+4)
15 of 12.1 and had isotactic propylene sequences.

Variations in the composition of the polymer were obtained principally by
changing the ratio of ethene to propene. Molecular weight of the polymer could
be increased by a greater amount of ethene and propene compared to the amount
of the polymerization catalyst. Dienes such as norbornene and vinyl norbornene
20 could be incorporated into the polymer by adding them continuously during
polymerization.

Example 2: Comparative ethylene/propylene polymerization where the propylene
residues are atactic.

25 Polymerizations were conducted in a 1 liter thermostatted continuous
feed stirred tank reactor using hexane as the solvent. The polymerization reactor
was full of liquid. The residence time in the reactor was typically 7 - 9 minutes

and the pressure was maintained at 400kpa. Hexane, ethene and propene were metered into a single stream and cooled before introduction into the bottom of the reactor. Solutions of all reactants and polymerization catalysts were introduced continuously into the reactor to initiate the exothermic polymerization.

5 Temperature of the reactor was maintained at 45°C by changing the temperature of the hexane feed and by using cooling water in the external reactor jacket. For a typical polymerization, the temperature of feed was about -10°C. Ethene was introduced at the rate of 45 gms/min and propene was introduced at the rate of 310 gms/min. The polymerization catalyst, dimethyl silyl bridged

10 (tetramethylcyclopentadienyl) cyclododecylamido titanium dimethyl activated 1:1 molar ratio with N', N'-Dimethyl anilinium-tetrakis(pentafluorophenyl)borate was introduced at the rate of 0.002780 gms/hr. A dilute solution of triisobutyl aluminum was introduced into the reactor as a scavenger of catalyst terminators: a rate of approximately 36.8 mole per mole of catalyst was adequate for this

15 polymerization. After five residence times of steady polymerization, a representative sample of the polymer produced in this polymerization was collected. The solution of the polymer was withdrawn from the top, and then steam distilled to isolate the polymer. The rate of formation of the polymer was 258 gms/hr. The polymer produced in this polymerization had an ethylene content

20 of 14.1 wt%, ML@125 (1+4) of 95.4.

Variations in the composition of the polymer were obtained principally by changing the ratio of ethene to propene. Molecular weight of the polymer could be increased by a greater amount of ethene and propene compared to the amount of the polymerization catalyst. These polymers are described as aePP in the

25 Tables below.

Example 3: Analysis and solubility of several second polymer components

In the manner described in Example 1 above, several second polymer components of the above specification were synthesized. These are described in the table below. Table 1 describes the results of the GPC, composition, ML and DSC analysis for the polymers.

TABLE 1

SPC	(Mn) by GPC	(Mw) by GPC	Ethylene wt% by IR	Heat of fusion J/g	Melting Point by DSC (°C)	ML (1+4)@1 25°C
SPC-1	102000	248900	7.3	71.9	84.7	14
SPC-2	124700	265900	11.6	17.1	43.0	23.9
SPC-3	121900	318900	16.4	7.8	42.2	33.1
SPC-4			11.1	25.73	63.4	34.5
SPC-5			14.7	13.2	47.8	38.4
Comparative Polymers						
EPR			47.8	not detected	not detected	40
aePP			11.7	not detected	not detected	23

Table 1: Analysis of the second polymer component and the comparative polymers

Table 2 describes the solubility of the second polymer component.

TABLE 2

SPC	Wt. % soluble at 23°C	Wt. % soluble at 31°C	Wt. % soluble at 40°C	Wt. % soluble at 48°C
SPC-1	1.0	2.9	28.3	68.5
SPC-2	6.5	95.7		
SPC-3	51.6	52.3	2.6	
SPC-4	18.7	83.6		
SPC-5	36.5	64.2		
Comparative Polymers				
EPR	101.7			
aePP	100.5			

5

Table 2: Solubility of fractions of the second polymer component. Sum of the fractions add up to slightly more than 100 due to imperfect drying of the polymer fractions.

Table 3 describes the composition of the fractions of the second polymer component obtained in Table 2. Only fractions which have more than 4% of the total mass of the polymer have been analyzed for composition.

5

TABLE 3

SPC	Composition: Wt% ethylene in fraction				
	soluble at 23°C	soluble at 31°C	soluble at 40°C	soluble at 48°C	soluble at 56°C
SPC-1			8.0	7.6	
SPC-2	12.0	11.2			
SPC-3	16.8	16.5			
SPC-4	13.2	11.2			
SPC-5	14.9	14.6			
Comparative					
EPR	46.8				
atactic ePP	11.8				

Table 3: Composition of fractions of the second polymer component obtained in Table 2. The experimental inaccuracy in determination of the ethylene content is
 10 believed to about 0.4 wt% absolute

Example 4:

A total of 72g of a mixture of the first polymer component and the second polymer component, as shown in the Table 4, column 2, were mixed in a Brabender
5 intensive mixture for 3 minutes at a temperature controlled to be within 185°C and 220°C. High shear roller blades were used for the mixing and approximately 0.4g of Irganox-1076, an antioxidant available from the Novartis Corporation, was added to the blend. At the end of the mixing, the mixture was removed and pressed out into a 6" x 6" mold into a pad 0.25" thick at 215°C for 3 to 5 minutes.
10 At the end of this period, the pad was cooled and removed and allowed to anneal for 3 to 5 days. Test specimens of the required dumbbell geometry were removed from this pad and evaluated on an Instron tester to produce the data shown in Table 4.

The first polymer component was Escorene 4292, a commercially available
15 homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas. The second polymer component was SPC-1 as characterized in Tables 1, 2 and 3 above.

TABLE 4

	Composition in grams of FPC and SPC-1								
FPC	64	56	48	40	32	24	16	8	0
SPC-1	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	4836	4243	3839	3274	2878	2475	2054	1705	1400
E = 25%	2782	3526	3460	3238	2863	2523	2146	1835	1502
E = 50%	2566	2539	2472	2589	2218	2135	1758	1501	1136
E =100%		2509	2434	2231	2169	1907	1642	1376	1136
E =150%				2239	2130	1844	1665	1407	1173
E =200%				2247	2105	1854	1679	1440	1197
E =250%				2245	2093	1887	1691	1478	1218
E =300%				2253	2066	1896	1699	1474	1231
E =350%				2251	2073	1905	1698	1476	1239
E =400%				2251	2137	1879	1708	1478	1218
E =450%				2247	2158	1869	1718	1474	1223
E =500%				2246	2177	1901	1726	1470	1279
E =550%					2229	2324	2350	2278	2261
E =600%						3072	3229	3159	2970
E =650%						3415	3538	3422	3010
E =700%						3691			3135
E =750%									3294

Table 4: Stress versus extension (E) data for blends of first polymer component
 5 and second polymer component where the second polymer component is

Component SPC-1 in the tables above. Shaded areas represent broken samples. Clear areas represent lack of data due to extension beyond machine limits.

Example 5:

- 5 The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas. The second polymer component was Component SPC-2 as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

TABLE 5

	Composition in grams of FPC and SPC-2								
FPC	64	56	48	40	32	24	16	8	0
SPC	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	4616	3477	2777	2221	1405	1012	705	488	326
E = 25%	2754	2863	2319	2178	1518	1143	822	634	472
E = 50%		2459	2221	1911	1517	1183	852	660	539
E =100%			2243	1872	1522	1236	897	675	552
E =150%			2261	1910	1546	1290	948	703	558
E =200%			2271	1947	1581	1345	1003	737	574
E =250%			2317	2037	1696	1486	1128	834	631
E =300%			2341	2061	1788	1579	1210	904	690
E =350%				2078	1919	1704	1313	995	778
E =400%				2167	2096	1864	1452	1106	894
E =450%				2221	2319	2069	1613	1239	1031
E =500%				2397	2597	2344	1810	1398	1186
E =550%					2976	2691	2060	1600	1350
E =600%					3611	3224	2443	1854	1547
E =650%							3660	2946	
E =700%									
E =750%									

Table 5: Stress versus extension (E) data for blends of first polymer component and second polymer component where the second polymer component is component SPC-2 in the tables above. Shaded areas with no data represent broken

samples. Clear areas represent lack of data due to extension beyond machine limits.

Example 6:

- 5 The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company. The second polymer component was Component SPC-3 as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

TABLE 6

	Composition in grams of FPC and SPC-3								
FPC	64	56	48	40	32	24	16	8	0
SPC-3	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	3700	3333	2427	1574	770	421	161	89	70
E = 25%	2614	2989	2229	1607	840	498	224	135	99
E = 50%		2428	1944	1632	895	542	263	167	121
E =100%		2399	1999	1644	945	575	281	180	131
E =150%		2405	2043	1648	989	608	294	185	136
E =200%			1995	1653	1069	675	329	188	135
E =250%					1140	741	372	195	128
E =300%					1195	807	423	209	124
E =350%					1244	866	474	229	125
E =400%					1273	925	528	255	129
E =450%						979	580	285	136
E =500%						1026	627	319	145
E =550%						1081	676	354	154
E =600%						1124	726	390	166
E =650%							781	424	181
E =700%							842	454	197
E =750%							911	488	217
E =800%							980	529	236
E =850%							1049	577	256
E =900%							1220	689	299
E =950%							1322	760	322

Table 6: Stress versus extension (E) data for blends of first polymer component and second polymer component where the second polymer component is Component SPC-3 in the tables above. Shaded areas with no data represent broken samples. Clear areas represent lack of data due to extension beyond
5 machine limits.

Example 7:

The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas.
10 The second polymer component was Component SPC-4 as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

TABLE 7

	Composition in grams of FPC and SPC-4								
FPC	64	56	48	40	32	24	16	8	0
SPC-4	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	4485	3719	3091	2387	1879	1372	950	717	527
E = 25%	3983	3467	2944	2413	1960	1467	1082	893	686
E = 50%	2691	2473	2264	2186	1818	1429	1062	896	728
E =100%		2448	2390	1951	1713	1387	1046	851	670
E =150%		2496	2436	1965	1742	1390	1065	854	671
E =200%		2523	2449	2001	1775	1411	1097	869	691
E =250%		2532	2456	2038	1790	1448	1141	894	700
E =300%		2537	2445	2070	1781	1496	1195	935	720
E =350%		2548	2434	2087	1765	1568	1268	991	791
E =400%		2564	2467	2152	1878	1682	1374	1089	877
E =450%		2552		2242	1998	1854	1522	1235	1032
E =500%				2407	2255	2101	1726	1416	1230
E =550%				2642	2603	2398	1990	1637	1444
E =600%				3048	3020	2689	2275	1882	1661
E =650%					3410	2983	2540	2116	1824
E =700%						3310	2730	2243	1821
E =750%						3741	3183	2569	2387

Table 7: Stress versus extension (E) data for blends of first polymer component and second polymer component where the second polymer component is Component SPC-4 in the tables above. Shaded areas with no data represent broken

samples. Clear areas represent lack of data due to extension beyond machine limits.

Example 8:

- 5 The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas. The second polymer component was a mixture of Component SPC-1 and Component SPC-5 as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

TABLE 8

	Composition in grams of FPC, SPC-1 and SPC-5								
FPC	32	28	24	20	16	12	8	4	0
SPC-1	32	28	24	20	16	12	8	4	0
SPC-5	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	2158	1705	1382	875	523	342	215	149	97
E = 25%	2208	1903	1533	1035	656	437	296	216	141
E = 50%	1977	1823	1510	1102	725	489	342	257	174
E =100%	1761	1655	1440	1154	798	546	379	286	200
E =150%	1775	1585	1412	1194	868	605	417	304	211
E =200%	1787	1582	1418	1236	942	669	465	329	219
E =250%	1793	1601	1441	1280	1020	734	521	364	229
E =300%	1802	1631	1475	1337	1103	801	585	410	245
E =350%	1819	1662	1524	1409	1190	873	653	468	267
E =400%	1841	1698	1592	1501	1290	955	729	530	297
E =450%	1862	1740	1678	1626	1408	1058	813	606	337
E =500%	1888	1757	1874	1791	1543	1187	920	697	387
E =550%	1904	1930	2235	2027	1730	1352	1077	813	448
E =600%	1935	2900	2627	2316	1988	1612	1335	998	521
E =650%	1977	3452	2939	2659	2460	1978	1652	1233	616
E =700%	2016		3159	3056		2530	2005	1492	759
E =750%			3377	3857			2446	1836	914
E =800%									1075
E =850%									1277
E =900%									

Table 8: Stress versus extension (E) data for blends of first polymer component and EPR in the tables above. Shaded areas with no data represent broken samples.

Example 9 (Comparative):

- 5 The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas. The second polymer component was Component EPR as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

10

TABLE 9

	Composition in grams of FPC and EPR								
FPC	64	56	48	40	32	24	16	8	0
EPR	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E=10%	3456	3125	2589	960	789	654	728	112	12
E = 25%		3358	3596	1122	999	890	754	244	18
E = 50%				1536	1356	1100	723	312	19
E =100%				2125	1681	1292	812	432	
E =150%					1674	1330	860		
E =200%					1744	1391	898		
E =250%									

- 15 Table 9: Stress versus extension (E) data for blends of first polymer component and EPR in the tables above. Shaded areas with no data represent broken samples.

Example 10 (Comparative):

The first polymer component was Escorene 4292, a commercially available homoisotactic polypropylene from Exxon Chemical Company, Houston, Texas. The second polymer component was aePP as characterized in Tables 1, 2 and 3 above. These components were mixed in the same manner as described for Example 4.

TABLE 10

	Composition in grams of FPC and aePP								
FPC	64	56	48	40	32	24	16	8	0
aePP	8	16	24	32	40	48	56	64	72
	Stress (psi)								
E =10%	3258	3012	2258	872	635	558	432	189	15
E = 25%			2785	1687	975	870	856	215	15
E = 50%					1012	912	816	256	27
E =100%					974	865	826	354	
E =150%						713	765		
E =200%									

While the illustrative embodiments of the invention have been described with particularity, it will be understood that various other modifications will be apparent to and can be readily made by those skilled in the art without departing from the spirit and scope of the invention. Accordingly, it is not intended that the scope of the claims appended hereto be limited to the examples and descriptions set forth herein but rather that the claims be construed as encompassing all the features of patentable novelty which reside in the present invention, including all features which would be treated as equivalents thereof by those skilled in the art to which the invention pertains.

CLAIMS

1. A composition comprising a blend of at least a first polymer component and a second polymer component, said blend comprising:
greater than 2% by weight of said first polymer component
5 comprising isotactic polypropylene, and
a second polymer component comprising a copolymer of propylene, and
at least one other alpha-olefin having less than 6 carbon atoms, said
copolymer comprising crystallizable propylene sequence and at least 75%
by weight propylene.
10
2. The composition of claim 1 wherein the first polymer component further comprises a comonomer.
3. The composition of claim 1 wherein the first polymer component is
15 predominately crystalline with a melting point by DSC equal to or above 115° C.
4. The composition of claim 1 wherein the alpha-olefin of the second polymer component comprises ethylene.
- 20 5. The composition of claim 1 wherein the second polymer component is comprised of about 5% to about 25% by weight alpha-olefin.
6. The composition of claim 5 wherein the alpha-olefin of the second polymer component comprises ethylene.
25
7. The composition of claim 1 wherein the second polymer component is comprised of from about 6% to about 18% by weight ethylene.

8. The composition of claim 1 wherein the crystallizable propylene sequences comprise isotactic propylene sequences.
- 5 9. The composition of claim 1 wherein the first polymer component has a melting point equal to or greater than about 130°C and the second polymer component has a melting point equal to or less than about 105°C.
- 10 10. The composition of claim 9 wherein the resultant blend has a glass transition temperature closer to that of the second polymer component and lower than the glass transition temperature of the first polymer component.
11. The composition of claim 1 wherein the second polymer component has a molecular weight distribution of about 2.0 to about 3.2.
- 15 12. The composition of claim 1 wherein the second polymer component has a melting point by DSC between about 30 C and about 100 C.
13. A thermoplastic polymer blend composition comprising:
20 from about 2% to about 95% by weight of a first thermoplastic polymer component comprising isotactic polypropylene, and
from about 5% to about 98% by weight of a second thermoplastic polymer component comprising a random copolymer of ethylene and propylene having a melting point by DSC between about 30 C
25 and about 100 C, said copolymer comprising crystallizable propylene sequences and up to about 25% by weight ethylene.

14. The compositions of claim 13 wherein said first thermoplastic polymer component further comprises a propylene - alpha-olefin copolymer.
15. The composition of claim 13 wherein the second thermoplastic polymer component comprises from about 6% to about 18% ethylene.
16. The composition of claim 13 wherein the blend composition has a glass transition temperature closer to that of the second polymer component and lower than the glass transition temperature of the first polymer component.
17. The composition of claim 13 wherein the second thermoplastic polymer component has a molecular weight distribution of about 2.0 to about 3.2.
18. A thermoplastic polymer blend composition comprising:
- a) from about 2% to about 95% by weight of a first thermoplastic polymer component selected from the group comprising isotactic polypropylene and propylene alpha-olefin copolymer, and
 - b) a second polymer composition comprising a blend of two propylene alpha-olefin copolymers. Wherein in one of said copolymers lies an alpha-olefin content of from 5% to 9% by weight and the other copolymer has an alpha-olefin content of from 10 wt% to 22 wt%.
19. The thermoplastic polymer blend of claim 18 where the alpha-olefin in the second polymer component is ethylene.

20. A process for preparing a thermoplastic polymer blend composition comprising:

- a. polymerizing propylene or a mixture of propylene and one or more monomers selected from a group consisting of C₂ or C₄ - C₁₀ alpha olefins in the presence of a polymerization catalyst wherein a substantially isotactic propylene polymer containing at least about 90% by weight polymerized propylene is obtained;
- b. polymerizing a mixture of ethylene and propylene, wherein a copolymer of ethylene and propylene is obtained comprising up to about 25% by weight ethylene and containing isotactically crystallizable propylene sequences; and
- c. blending the propylene polymer of step (a) with the copolymer of step (b) to form a blend.

21. The process of claim 18 wherein the isotactic propylene polymer has melting point greater than 130°C.

22. The process of claim 18 wherein the copolymer comprises from about 6% to about 18% by weight ethylene.

23. The process of claim 18 wherein the copolymer has a melting point by DSC between about 30° C and about 100° C.

24. The resultant blend of the process of claim 18 wherein the blend has a glass transition temperature closer to that of the second polymer component and lower than the glass transition temperature of the first polymer component.

25. The process of claim 18 wherein the copolymer of ethylene and propylene is a random copolymer having a molecular weight distribution of about 2.0 to about 3.2.

5 26. The process of claim 18 wherein the ethylene and propylene are polymerized in the presence of the isotactic propylene polymer composition of step (a) in a reactor wherein a reactor blend is formed.

10 27. The process of claim 18 wherein the ethylene and propylene are polymerized in the presence of a metallocene catalyst.

28. The process of claim 18 wherein the propylene is polymerized in the presence of a metallocene or a Ziegler-Natta catalyst.

15 29. The process of claim 18 wherein from about 2% to about 95% by weight isotactic propylene polymer is blended with about 5% to about 98% by weight copolymer of ethylene and propylene.

20 30. The thermoplastic polymer blend composition produced by the process of claim 18.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/09802

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L23/10 C08F23/12 C08F23/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 1 342 647 A (SHELL INT RESEARCH) 3 January 1974 see claim 1	1
X	US 3 998 911 A (STRAMETZ HELMUT ET AL) 21 December 1976 see claim 3	1
A	EP 0 550 214 A (EXXON RESEARCH ENGINEERING CO) 7 July 1993 see the whole document	1-30
A	US 4 461 872 A (SU AARON C L) 24 July 1984 cited in the application see the whole document	1-30
-/--		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

22 December 1998

Date of mailing of the international search report

30/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Golde, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/09802

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 3 888 949 A (SHIH CHI-KAI) 10 June 1975 cited in the application see the whole document -----</p>	1-30

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 98/09802

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1342647	A	03-01-1974	NL 7001827 A	12-08-1971
			BE 762342 A	02-08-1971
			CA 982295 A	20-01-1976
			DE 2105683 A	26-08-1971
			FR 2078327 A	05-11-1971
US 3998911	A	21-12-1976	DE 2417093 A	06-11-1975
			AR 208402 A	27-12-1976
			AU 7988975 A	14-10-1976
			BE 827680 A	08-10-1975
			CA 1052933 A	17-04-1979
			DK 147475 A	09-10-1975
			FR 2266721 A	31-10-1975
			GB 1508033 A	19-04-1978
			IN 140973 A	08-01-1977
			JP 50142652 A	17-11-1975
			LU 72222 A	02-02-1977
			NL 7503966 A	10-10-1975
			ZA 7502172 A	28-04-1976
EP 0550214	A	07-07-1993	BR 9205045 A	22-06-1993
			CA 2083664 A	21-06-1993
			DE 69222514 D	06-11-1997
			DE 69222514 T	07-05-1998
			ES 2106837 T	16-11-1997
			JP 5311081 A	22-11-1993
US 4461872	A	24-07-1984	CA 1222087 A	19-05-1987
			EP 0119508 A	26-09-1984
			JP 59157137 A	06-09-1984
US 3888949	A	10-06-1975	NL 7408291 A	24-12-1974



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08L 23/10, 23/12, 23/16</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/07788 (43) International Publication Date: 18 February 1999 (18.02.99)</p>
<p>(21) International Application Number: PCT/US98/09802 (22) International Filing Date: 23 July 1998 (23.07.98) (30) Priority Data: 08/910,001 12 August 1997 (12.08.97) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520-5200 (US). (72) Inventors: DATTA, Sudhin; 2203 Driscoll Street, Houston, TX 77019 (US). GADKARI, Avinash, C.; 13827 Rosebranch Court, Houston, TX 77059 (US). COZEWITH, Charles; 4810 Welford Drive, Bellaire, TX 77401 (US). (74) Agents: SCHNEIDER, John, E. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).</p>		<p>(81) Designated States: AU, BR, CA, CN, JP, KR, MX, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With a revised version of the international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the revised version of the international search report: 10 June 1999 (10.06.99)</p>
<p>(54) Title: THERMOPLASTIC POLYMER BLENDS OF ISOTACTIC POLYPROPYLENE AND ALPHA-OLEFIN/PROPYLENE COPOLYMERS (57) Abstract Thermoplastic polymer blend compositions comprising an isotactic polypropylene component and an alpha-olefin and propylene copolymer, said copolymer comprising crystallizable alpha-olefin sequences. In a preferred embodiment, improved thermoplastic polymer blends are provided comprising from about 35 % to about 85 % isotactic polypropylene and from about 30 % to about 70 % of an ethylene and propylene copolymer, wherein said copolymer comprises isotactically crystallizable propylene sequences and is predominantly propylene. The resultant blends manifest compatibility characteristics, increased tensile strength, and improved process characteristics, e.g., a single melting point.</p>		

*(Referred to in PCT Gazette No. 23/1999, Section II)

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/09802

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L23/10 C08L23/12 C08L23/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 1 342 647 A (SHELL INT RESEARCH) 3 January 1974 see claim 1	1
X	US 3 998 911 A (STRAMETZ HELMUT ET AL) 21 December 1976 see claim 3	1
A	EP 0 550 214 A (EXXON RESEARCH ENGINEERING CO) 7 July 1993 see the whole document	1-30
A	US 4 461 872 A (SU AARON C L) 24 July 1984 cited in the application see the whole document	1-30
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

8 February 1999

Date of mailing of the international search report

20.04.99

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Golde, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/09802

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 3 888 949 A (SHIH CHI-KAI) 10 June 1975 cited in the application see the whole document -----</p>	1-30

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/09802

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1342647	A	03-01-1974	NL 7001827 A	12-08-1971
			BE 762342 A	02-08-1971
			CA 982295 A	20-01-1976
			DE 2105683 A	26-08-1971
			FR 2078327 A	05-11-1971

US 3998911	A	21-12-1976	DE 2417093 A	06-11-1975
			AR 208402 A	27-12-1976
			AU 7988975 A	14-10-1976
			BE 827680 A	08-10-1975
			CA 1052933 A	17-04-1979
			DK 147475 A	09-10-1975
			FR 2266721 A	31-10-1975
			GB 1508033 A	19-04-1978
			IN 140973 A	08-01-1977
			JP 50142652 A	17-11-1975
			LU 72222 A	02-02-1977
			NL 7503966 A	10-10-1975
			ZA 7502172 A	28-04-1976

EP 0550214	A	07-07-1993	BR 9205045 A	22-06-1993
			CA 2083664 A	21-06-1993
			DE 69222514 D	06-11-1997
			DE 69222514 T	07-05-1998
			ES 2106837 T	16-11-1997
			JP 5311081 A	22-11-1993

US 4461872	A	24-07-1984	CA 1222087 A	19-05-1987
			EP 0119508 A	26-09-1984
			JP 59157137 A	06-09-1984

US 3888949	A	10-06-1975	NL 7408291 A	24-12-1974
